

ONEIDA COUNTY FORESTRY DEPARTMENT

CORDWOOD WEIGHT CONVERSION FACTORS POUNDS PER CORD

<u>SPECIES</u>	<u>GREEN WEIGHT</u>	
	<u>Lb/cd</u>	<u>Tons/cd</u>
Hemlock	4800	2.40
Tamarack	4650	2.33
Red Pine	4500	2.25
Jack Pine	4250	2.13
White Pine	4200	2.10
Spruce	4000	2.00
Cedar	3150	1.58
Red Oak	5850	2.75
Yellow Birch	5350	2.68
Hard Maple	5100	2.55
Ash	4600	2.30
Soft Maple	4550	2.28
Basswood	3850	1.93
Aspen	4500	2.25
Balsam	4250	2.13
White Birch	4800	2.40
Mixed Hardwood	4900	2.45